



ETA-Danmark A/S
Göteborg Plads 1
DK-2150 Nordhavn
Tel. +45 72 24 59 00
Internet www.etadanmark.dk

Authorised and notified
according to Article 29 of the
Regulation (EU)
No 305/2011 of the European
Parliament and of the Council
of 9 March 2011

MEMBER OF EOTA



European Technical Assessment ETA-20/1007 of 2020/12/08

I General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: ETA-Danmark A/S

Trade name of the construction product:

PipeBloc EL

Product family to which the above construction product belongs:

Fire Stopping, Fire Sealing & Fire Protective Products.
Fire Retardant Products

Manufacturer:

FSi Ltd
Westminster Industrial Estate
Tamworth Rd
Measham
GB-Swadlincote DE12 7DS
Telephone: +44 1530 515130
www.FSiLtd.com

Manufacturing plant:

FSi Ltd
Westminster Industrial Estate
Tamworth Rd
Measham
GB-Swadlincote DE12 7DS
Telephone: +44 1530 515130
www.FSiLtd.com

This European Technical Assessment contains:

21 pages including 1 annex which form an integral part of the document

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of:

EAD 350454-00-1104 Firestopping and fire sealing products, Penetration Seals, Issued September 2017

This version replaces:

-

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full [except the confidential Annex(es) referred to above]. However, partial reproduction may be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

1 Technical Description of the Product

- 1) PipeBloc EL is installed around combustible pipes to form a penetration seal used to reinstate the fire resistance performance of wall and floor constructions, where they have been provided with apertures for the penetration of combustible pipe services.
- 2) PipeBloc EL is installed around the pipe at the soffit and upper face of floors and both faces of walls, depending on application and by applying a number of passes to reach the required thickness. Fixing specifications and number of passes are detailed in Annex A.
- 3) PipeBloc EL can be used with Pyrocoustic Sealant to seal the space between the combustible pipe and the aperture to close gap sizes as specified in Annex A.

2 Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter EAD)

The intended use of PipeBloc EL is to reinstate the fire resistance performance of wall and floor constructions, where they are penetrated by various combustible pipe services.

The specific elements of construction that the PipeBloc EL may be used is as follows:

Flexible walls: The wall must have a minimum thickness of 100 mm and comprise timber or steel studs line on both faces with minimum 2 layers of 12.5 mm thick, 'Type F' Gypsum boards according to EN 520. In timber stud walls, no part of the penetration seal shall be closer than 100mm to a stud, and minimum 100 mm of insulation of class A1 or A2 according to EN 13501-1, is provided within the cavity between the penetration seal and the stud.

Rigid walls: The wall must have a minimum thickness of 100 mm and comprise of concrete, aerated concrete or masonry, with a minimum density of 650 km/m³.

Rigid floor: The floor must have a minimum thickness of 150 mm and comprise of concrete, aerated concrete or masonry, with a minimum density of 650 km/m³.

- 1) The supporting construction must be classified in accordance with EN 13501-2 for the required fire resistance period.
- 2) The system PipeBloc EL may be used to provide a penetration seal with specific combustible pipes, single only (for details see Annex A).
- 3) Apertures in the separating element shall be maximum oversize with respect to the pipe diameter according to the tables listed in Annex A. The remaining annular space/gap shall be infilled with Pyrocoustic Sealant. Apertures for the penetration of pipes shall be separated by a minimum of 200 mm.
- 4) The provisions made in this European Technical Assessment are based on an assumed working life of the PipeBloc EL of 10 years, The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.
- 5) Services in walls shall be supported at maximum 400mm from the face of the separating element for walls, and 400mm above the surface of the floor.

Use Category

Type X: Intended for use in conditions exposed to weathering.

3 Performance of The Product And References To The Methods Used For Its Assessment

| Characteristic | Assessment of characteristic |
|--|------------------------------|
| BWR 1 Mechanical resistance and stability | |
| BWR 2 Safety in case of fire | |
| Reaction to fire | See clause 1.1 |
| Resistance to fire | See Clause 1.2 |
| BWR 3 Hygiene, Health and the Environment | |
| Release of dangerous substances | See Clause 2.1 |
| BWR 4 Safety in use | |
| Durability and serviceability | See Clause 3.1 |
| BWR 5 Protection against noise | |
| BWR 6 Energy, Economy and Heat Retention | |

3.1 Safety in case of fire

3.1.1 Reaction to fire

Pipebloc EL is classified **E** in accordance with EN 13501-1

3.1.2 Resistance to fire

See Annex A.

3.2 Hygiene, Health and the Environment.

3.2.1 Content and release of Dangerous Substances

FSI Ltd have presented a declaration that PipeBloc EL releases no dangerous substances in compliance with Council Directive 67/548/EEC of 1st June 1965 on the approximation of the laws, regulations and administrative provisions of the Member States relating to restrictions on the marketing and use of certain dangerous substances and preparations (incl. All amendments and adaptations).

The manufacturer declares that the product contains no dangerous substances according to current European and National regulations.

FSI Ltd has submitted a written declaration that the product and/or constituents of the product contains no substances which have been classified as dangerous according to Directive 67/548/EEC and Regulation (EC) No. 1272/2008 and listed in the 'indicative list on dangerous substances' of the EGDS – taking into account the installation conditions of the construction product and the release scenarios resulting from there.

In addition to the specific clauses relating to dangerous substances contained in this European Technical Assessment, there may be other requirements applicable to the products falling within its scope (e.g.

transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Regulation, these requirements need also to be complied with, when and where they apply.

The use category of PipeBloc EL in relation to BWR 3 (Hygiene, health and environment) is IA1, S/W3.

3.3 Safety and accessibility in use

3.3.1 Durability

PipeBloc EL has been tested in accordance with EOTA Technical Report - TR024 – Edition November 2006, EAD 350454-00-1104, Fire Stopping and Fire Sealing Products-Penetration Seals for type X, environmental conditions: Products for penetration seals intended for outdoor use exposed to weathering – rain, UV, high temperatures, frost and frost-thaw in winter.

4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to the decision 1999/454/EC of the European Commission the system of assessment and verification of constancy of performance (see Annex V to the Regulation (EU) No 305/2011) given in the following table apply:

| Products | Intended use(s) | AVCP System |
|---|--|--------------------|
| Fire stopping and fire sealing products | For fire compartmentation and / or fire protection or fire performance | System 1 |

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at ETA-Danmark A/S prior to CE marking

Issued in Copenhagen on 2020-12-08 by



Thomas Bruun

Managing Director, ETA-Danmark

Annex A

Resistance to Fire Classification of PipeBloc EL

A.1 Intumescent Thickness


The permitted thickness of the intumescent material for various ranges of pipe diameters:

| Intumescent Thickness | |
|-----------------------|-------------------------|
| Pipe Diameter | Intumescent Material |
| ø 32 mm - ø 50 mm | 1 off 40 mm (W) x 2 (T) |
| ø 51 mm - ø 82 mm | 2 off 40 mm (W) x 2 (T) |
| ø 83 mm - ø 115 mm | 3 off 40 mm (W) x 2 (T) |
| ø 116 mm - ø 160 mm | 4 off 40 mm (W) x 2 (T) |
| ø 161 mm - ø 200 mm | 5 off 40 mm (W) x 2 (T) |
| ø 201 mm - ø 250 mm | 6 off 40 mm (W) x 2 (T) |

A.2 Floor construction with thickness of minimum 150 mm

A.2.1 Penetration seal with PipeBloc EL installed within both sides of rigid floor


Construction details: Combustible pipes installed with a single PipeBloc EL within both sides. Maximum annular space according to the tables listed in A.2.1.1 to A.2.1.3 filled with Pyrocooustic sealant.





A.2.1.1 PVC-U pipes with PipeBloc EL installed within both sides of rigid floor

PVC pipes according to EN 1452 with PipeBloc EL.

| PipeBloc EL, Friction Fitted Flush to Both Sides of Rigid Floor (min 150 mm thick) PVC Pipes | | | |
|---|----------------------------|---------------------------|--------------------------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| PVC Pipe 32 mm \varnothing 1.8 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| PVC Pipe 40 mm \varnothing 1.8 mm wall thickness | | | |
| PVC Pipe 50 mm \varnothing 1.8 mm wall thickness | | | |
| PVC Pipe 200 mm \varnothing 7.7 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | E 120 U/C EI 90 U/C |
| PVC Pipe 200 mm \varnothing 9.6 mm wall thickness | | | EI 60 U/C |








A.2.1.2 PP pipes with PipeBloc EL installed within both sides of rigid floor

PP pipes according to EN 1451 with PipeBloc EL.

| PipeBloc EL, Friction Fitted Flush to Both Sides of Rigid Floor (min 150 mm thick) PP Pipes | | | |
|--|----------------------------|---------------------------|------------------------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| PP Pipe 32 mm \varnothing 2.9 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| PP Pipe 40 mm \varnothing 2.9 mm wall thickness | | | |
| PP Pipe 50 mm \varnothing 2.9 mm wall thickness | | | |
| PP Pipe 200 mm \varnothing 4.9 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | E 20U/C EI 15U/C |
| PP Pipe 200 mm \varnothing 18.2 mm wall thickness | | | E 120U/C EI 90U/C |






A.2.1.3 HDPE pipes with PipeBloc EL installed within both sides of rigid floor

HDPE pipes according to EN 1519 with PipeBloc EL.


| PipeBloc EL, Friction Fitted Flush to Both Sides of Rigid Floor (min 150 mm thick) HDPE Pipes | | | |
|--|----------------------------|---------------------------|-----------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| HDPE Pipe 32 mm \varnothing 2.9 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| HDPE Pipe 40 mm \varnothing 2.9 mm wall thickness | | | |
| HDPE Pipe 50 mm \varnothing 2.9 mm wall thickness | | | |
| HDPE Pipe 200 mm \varnothing 4.9 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | |
| HDPE Pipe 200 mm \varnothing 11.4 mm wall thickness | | | |



A.3 Wall construction with thickness of minimum 100 mm

A.3.1 Penetration seal with PipeBloc EL installed within both sides of flexible or rigid wall


Construction details: Combustible pipes installed with a single PipeBloc EL within both sides. Maximum annular space according to the tables listed in A.3.1.1 to A.3.1.3 filled with Pyrocoustic sealant.




A.3.1.1 PVC pipes with PipeBloc EL installed within both sides of flexible or rigid wall

PVC pipes according to EN 1452 with PipeBloc EL.

| PipeBloc EL, Friction Fitted Flush to Both Sides of Flexible or Rigid Wall (min 100 mm thick) PVC Pipes | | | |
|--|----------------------------|---------------------------|-----------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| PVC Pipe 32 mm \varnothing 1.8 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| PVC Pipe 40 mm \varnothing 1.8 mm wall thickness | | | |
| PVC Pipe 50 mm \varnothing 1.8 mm wall thickness | | | |
| PVC Pipe 160 mm \varnothing 6.2 mm wall thickness | 4 off 40 mm (W) x 2 mm (T) | 10 | EI 90 U/C |
| PVC Pipe 160 mm \varnothing 9.5 mm wall thickness | | | EI 120 U/C |
| PVC Pipe 200 mm \varnothing 7.7 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | |
| PVC Pipe 200 mm \varnothing 9.6 mm wall thickness | | | |








A.3.1.2 PP pipes with PipeBloc EL installed within both sides of flexible or rigid wall

PP pipes according to EN 1451 with PipeBloc EL.

| PipeBloc EL, Friction Fitted Flush to Both Sides of Flexible or Rigid Wall (min 100 mm thick) PP Pipes | | | |
|---|----------------------------|---------------------------|--------------------------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| PP Pipe 32 mm \varnothing 2.9 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| PP Pipe 40 mm \varnothing 2.9 mm wall thickness | | | |
| PP Pipe 50 mm \varnothing 2.9 mm wall thickness | | | |
| PP Pipe 160 mm \varnothing 4.0 mm wall thickness | 4 off 40 mm (W) x 2 mm (T) | 10 | E 120 U/C |
| PP Pipe 160 mm \varnothing 14.6 mm wall thickness | | | EI 120 U/C |
| PP Pipe 200 mm \varnothing 4.9 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | E 120 U/C |
| PP Pipe 200 mm \varnothing 18.2 mm wall thickness | | | EI 120 U/C |
| PP Pipe 250 mm \varnothing 10.1 mm wall thickness | 6 off 40 mm (W) x 2 mm (T) | 14 | E 120 U/C EI 20 U/C |





A.3.1.3 PE pipes with PipeBloc EL installed within both sides of flexible or rigid wall

PE pipes according to EN ISO 15494 with PipeBloc EL.

| PipeBloc EL, Friction Fitted Flush to Both Sides of Flexible or Rigid Wall (min 100 mm thick) PE Pipes | | | |
|---|----------------------------|---------------------------|-----------------------|
| Penetration Specification | Wrap Size / Number | Annulus Space (mm) | Classification |
| PE Pipe 32 mm \varnothing 2.9 mm wall thickness | 1 off 40 mm (W) x 2 mm (T) | 4 | EI 120 U/C |
| PE Pipe 40 mm \varnothing 2.9 mm wall thickness | | | |
| PE Pipe 50 mm \varnothing 2.9 mm wall thickness | | | |
| PE Pipe 160 mm \varnothing 4.9 mm wall thickness | 4 off 40 mm (W) x 2 mm (T) | 10 | EI 15 U/C |
| PE Pipe 160 mm \varnothing 9.5 mm wall thickness | | | EI 90 U/C |
| PE Pipe 200 mm \varnothing 4.9 mm wall thickness | 5 off 40 mm (W) x 2 mm (T) | 12 | EI 15 U/C |
| PE Pipe 200 mm \varnothing 18.4 mm wall thickness | | | EI 120 U/C |

